

INVESTOR IN PEOPLE

The Patent Office
 Concept House
 Cardiff Road
 Newport
 South Wales
 NP10 8QQ

11 OCT 2004

WIPO


PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated 21 September 2004


PRIORITY DOCUMENT
 SUBMITTED OR TRANSMITTED IN
 COMPLIANCE WITH
 RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

No Charge

Patents Form 1/77

Patents Act 1977
(Rule 16)



1/77
03OCT03 001718-1 000395
P01/7700 0.00-0323095.0

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference

P17499GB-LH/mf

2. Patent application number

(The Patent Office will fill this part in)

02 OCT 2003

0323095.0

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Minebea Co. Ltd.,
4106-73 Oaza Miyota,
Miyota-machi, Kitasaku-gun,
Nagano 389-0293,
Japan.

08719387001

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

Japan

4. Title of the invention

Self-Lubricating Bearings

5. Name of your agent (if you have one)

Forrester Ketley & Co.

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Forrester House
52 Bounds Green Road
London
N11 2EY

Patents ADP number (if you know it)

133001

6. Priority: Complete this section if you are declaring priority from one or more earlier patent applications, filed in the last 12 months.

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. Divisionals, etc: Complete this section only if this application is a divisional application or resulted from an entitlement dispute (see note d)

Number of earlier UK application

Date of filing
(day / month / year)

8. Is a Patents Form 7/77 (Statement of inventorship and of right to grant of a patent) required in support of this request?

Answer YES if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

YES

Otherwise answer NO (See note d)

Patents Form 1/77

9. Accompanying documents: A patent application must include a description of the invention. Not counting duplicates, please enter the number of pages of each item accompanying this form:

Continuation sheets of this form -

Description 8 -

Claim(s) 3 -

Abstract 1 -

Drawing(s) 3 + 3 *fm*

10. If you are also filing any of the following, state how many against each item.

Priority documents -

Translations of priority documents -

Statement of inventorship and right to grant of a patent (Patents Form 7/77) -

Request for a preliminary examination and search (Patents Form 9/77) 1 -

Request for a substantive examination (Patents Form 10/77) 1 -

Any other documents (please specify) -

11. I/We request the grant of a patent on the basis of this application.

Signature(s) Forrester Ketley & Co. *Forrester Ketley & Co.*

Date 2 October 2003

12. Name, daytime telephone number and e-mail address, if any, of person to contact in the United Kingdom

HOARTON, Lloyd
(020) 8889 6622

fkldon@forresters.co.uk

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered YES in part 8, a Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- Part 7 should only be completed when a divisional application is being made under section 15(1), or when an application is being made under section 31(1), 32(1) or 33(1) following an entitlement dispute. For completing part 7 see the instructions on the back of the form.

PATENTS ACT 1977

Agent's Ref: P17499GB-LDH/mf

“SELF-LUBRICATING BEARINGS”

This invention relates to self-lubricating bearings and more particularly to self-lubricating bearings for use in low pressure or stress, high-frequency, small amplitude motion applications.

Self-lubricating bearings typically comprise a housing having a liner which is in sliding contact with a counterface. In the case of spherical bearings, the counterface comprises a ball and the housing is provided with a self-lubricating liner comprising woven or meshed fibres suffused with a resin to hold together a quantity of PTFE or other self-lubricating material. Such PTFE-rich liner systems are well-known and have been used in the past, particularly in low stress, high frequency, small amplitude motion applications for spherical bearings. The difficulties in providing self-lubricating bearings with sufficiently long life have been addressed and various solutions proposed and implemented including the approach taken in GB2170279 - the resultant bearing consisting of an extremely hard counterface surface consisting of a thick and hard coating at least 50 μm thick and having a surface finish or roughness of not greater than 50nm. GB2170279 discloses the use of surface finishes leaving a roughness in the order of 10-20nm at best.

GB2170279 teaches the use of a counterface with both extreme hardness and smoothness. The extreme hardness is specified as being not less than 1000VPN, with the hardness preferably being at least 1100 VPN – it should be noted that this hardness level corresponds to a tungsten carbide coated material.

Low stress, high frequency, small amplitude motion applications such as ground transport suspension systems and helicopter flying control and rotor systems have been thought for many years to require the technology disclosed in GB2170279 - i.e. a bearing having a counterface of extreme hardness and smoothness. The particular thinking behind adopting the extreme hardness in the counterface is to stop debris which includes hard materials such as particles of resin from the liner and metal from the counterface from damaging the surface finish of the counterface. As soon as the surface finish of the counterface is damaged, those irregularities or rough areas further damage the liner creating more liner debris resulting in increased backlash in the bearing leading to a reduced bearing life.

The general thinking has, therefore, been that the counterface surface must be made harder than the hard debris which results in the very hard counterface surface required in GB2170279. This requirement has previously necessitated the use of thick ($>50\mu\text{m}$) coatings which can only be machined after application. Any deviation from the characteristics specified in GB2170279, particularly with regard to the hardness and surface finish of the counterface, has therefore been regarded as unadvisable if one wishes to produce a bearing with a life comparable with that demonstrated in GB2170279 when used in low pressure or stress, high-frequency, small amplitude motion applications.

It is an object of the present invention to provide a self-lubricating liner which does not suffer from the requirement to use a counterface of extreme hardness and which provides at least comparable performance and life duration under the same operating conditions as disclosed in GB2170279.

Accordingly, one aspect of the present invention provides a self-lubricating bearing for use in low pressure, high frequency, small amplitude applications, the bearing having a self-lubricating liner and a counterface surface in close sliding contact therewith, the counterface surface having a surface finish of less than 20nm and a hardness of less than in the region of 1000VPN.

Preferably, the surface finish of the counterface surface is in the range of 5nm to 20nm.

Conveniently, the counterface surface comprises a coating on a curved surface having an electrolytically ground finish.

Advantageously, the coating has a thickness of between 1-5 μ m over the electrolytically ground finish.

Preferably, the coating is a chemical deposition coating, a physical vapour deposition coating or an ion plating coating.

20

Conveniently, the bearing is a spherical bearing.

Advantageously, the spherical bearing includes a ball, the ball providing the counterface surface.

25

Preferably, the operating conditions, in use, are at stresses of less than 35MPa, at a frequency of at least 0.1 Hz and with amplitudes comprising small angular motions of less than $\pm 12^\circ$ rotation.

Another aspect of the present invention provides a method of constructing a self-lubricating bearing comprising the steps of: providing a self-lubricating liner with a curved surface; providing a counterface having a curved surface; electrolytically grinding the curved surface of the counterface to a surface finish of less than 20nm to produce a counterface surface having a hardness of less than 1000VPN; and placing the curved surfaces of the liner and the counterface surface in sliding contact with one another.

Conveniently, the curved surfaces are correspondingly curved surfaces.

A further aspect of the present invention provides a method of operating a self-lubricating bearing having a self-lubricating liner and a counterface surface in close sliding contact therewith, the counterface surface having a surface finish of less than 20nm and a hardness of less than 1000VPN, wherein the operating conditions are at stresses of less than 35MPa, at a frequency of at least 0.1 Hz and with amplitudes comprising small angular motions of less than $\pm 12^\circ$ rotation.

In order that the present invention may be more readily understood, embodiments thereof will now be described, by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a cross-section of a detail of a self-lubricating bearing embodying the present invention; and

Figure 2 is a graphical comparison of wear test results of bearings embodying the present invention and known bearings.

Figure 3 is a graphical representation of wear test results of bearings embodying the present invention and known bearings.

5 Referring to Figure 1, a self-lubricating spherical bearing embodying the present invention is particularly designed for use under the conditions of low pressure or stress, high-frequency and small amplitude motion. Such conditions are, more particularly: at stresses of less than 35MPa, at a frequency of at least 0.1 Hz (helicopter applications are typically 5 to 30 Hz) and with
10 amplitudes comprising small angular motions of less than $\pm 12^\circ$ rotation and tilt of $\pm 5^\circ$. Such conditions are typically found in helicopter flying control and rotor systems and ground transport suspension systems. The self-lubricating spherical bearing embodying the present invention comprises a housing 1, having a spherical bearing surface 2 upon which a liner system 3 is bonded. A
15 ball 4 having a counterface surface 5 in close contact with the liner system 3 sits in and is typically restrained in the housing. The present invention is applicable to other forms of self-lubricating bearings and not exclusively to spherical bearings. Examples of other forms of bearings having a sliding surface in sliding contact with a counterface include cylindrical journal
20 bearings and flat contact bearings.

There is a sliding contact between the counterface 5 and the sliding surface 6 of the liner system 3.

25 The liner system 3 comprises a PTFE-rich self-lubricating liner system. The liner system is a low coefficient of friction liner system such as produced by NMB Minebea and consists of an enriched PTFE surface on a PTFE/Resin matrix, reinforced by a plain Nomex (Trade Mark) weave.

In direct contrast to the teaching of GB2170279, the counterface surface 5 does not have the extreme high hardness required in GB2170279. The counterface surface 5 of a preferably heat treated steel alloy ball as per AMS5630, has a hardness of 56Rc to 62Rc (650 to 750 VPN). Further, the counterface surface 5 is prepared to have a surface roughness in the order of 5nm and preferably in the range of 5nm to 20nm.

The improved texture of the surface, the reduction in surface finish defects, in combination with the enriched PTFE surface of the liner is extremely important to the invention since it removes the requirement, hitherto thought to be essential, of extreme hardness in the counterface surface as specified in GB2170279. By adopting a surface finish in the range of 5nm to 20nm, it has been surprisingly found that the counterface surface 5, even when softer than the extreme hardnesses quoted in GB2170279, in combination with the liner system creates less damage to the counterface surface and so does not destroy the good surface finish of the counterface surface 5 leading to a longer life bearing.

The most preferred method of achieving the requisite surface finish in the range of 5nm to 20nm is by electrolytic grinding as set out in EP-A-1078714. This method has not previously been used to improve the surface finish on spherical bearings. After manufacture and using conventional bearing finishing techniques a surface finish in the region of 40nm would be achieved whereas the electrolytic grinding method results in a much improved surface finish in the order of 5nm to 20nm.

A further improvement in surface finish and wear properties can be realised by utilising a grinding process at a critical vacuum level of

between 1-5 μ m over the electrolytically ground finish. Physical vapour deposition coatings could not be used with the bearing specified in GB2170279 because the necessary hardness for the coating – comprising the counterface surface – is not achievable at the low coating thicknesses produced by such deposition techniques. In contrast, because the claimed invention does not require a coating of extreme hardness, chemical or vapour deposition and ion plating techniques can be readily used. The physical vapour deposition coating gives rise to a counterface surface having a hardness in the region of 1000 VPN – still lower than the extreme hardness quoted in GB2170279.

10

Test results have shown improved bearing life for bearings embodying the present invention compared to like-tests carried out on bearing surfaces without the improved surface finish of 20nm or less. The results shown in Figure 2 show the range of wear results achieved for two different classes of bearing – the conventional finish (in the region of 70nm) and the finish on bearings embodying the present invention which is in the region of 5 to 20nm.

15

Further, referring to Figure 3, the wear test results are shown for the following bearings:

20

Example 1 comprises a bearing having a heat treated steel alloy ball as per AMS5630 having a hardness of 56Rc to 62Rc (650 to 750 VPN) provided with a conventional surface finish (in the region of 70nm);

25

Example 2 comprises a bearing having another heat treated steel alloy ball as per AMS5630 having a hardness of 56Rc to 62Rc (650 to 750 VPN) provided with a conventional surface finish (in the region of 70nm);

Example 3 comprises a bearing having a heat treated steel alloy ball as per AMS5630 having a hardness of 56Rc to 62Rc (650 to 750 VPN) provided with an electrolytically ground surface finish (of less than 20nm) with no coating;

Example 4 comprises a bearing having a heat treated steel alloy ball as per AMS5630 having a hardness of 56Rc to 62Rc (650 to 750 VPN) provided with an electrolytically ground surface finish (of less than 20nm) and a physical vapour deposition coating;

5 Example 5 comprises a bearing having another heat treated steel alloy ball as per AMS5630 having a hardness of 56Rc to 62Rc (650 to 750 VPN) provided with an electrolytically ground surface finish (of less than 20nm) and a physical vapour deposition coating;

10 Example 6 comprises a bearing having a ball manufactured in accordance with GB2170279 with no coating; and

Example 7 comprises a bearing having a ball with a tungsten carbide coating manufactured in accordance with GB2170279.

15 It should be noted that only Examples 3, 4 and 5 comprise embodiments of the present invention.

In the present specification "comprises" means "includes or consists of" and "comprising" means "including or consisting of".

20 The features disclosed in the foregoing description, or the following claims, or the accompanying drawings, expressed in their specific forms or in terms of a means for performing the disclosed function, or a method or process for attaining the disclosed result, as appropriate, may, separately, or in any combination of such features, be utilised for realising the invention in diverse
25 forms thereof.

CLAIMS:

1. A self-lubricating bearing for use in low pressure, high frequency, small amplitude applications, the bearing having a self-lubricating liner and a counterface surface in close sliding contact therewith, the counterface surface having a surface finish of less than 20nm and a hardness of less than in the region of 1000VPN.
2. A self-lubricating bearing according to Claim 1, wherein the surface finish of the counterface surface is in the range of 5nm to 20nm.
3. A self-lubricating bearing according to Claim 1 or 2, wherein the counterface surface comprises a coating on a curved surface having an electrolytically ground finish.
4. A self-lubricating bearing according to Claim 3, wherein the coating has a thickness of between 1-5 μ m over the electrolytically ground finish.
5. A self-lubricating bearing according to Claim 3 or 4, wherein the coating is a chemical deposition coating, a physical vapour deposition coating or an ion plating coating.
6. A self-lubricating bearing according to any preceding claim, wherein the bearing is a spherical bearing.
7. A self-lubricating bearing according to Claim 7, wherein the spherical bearing includes a ball, the ball providing the counterface surface.

8. A self-lubricating bearing according to any preceding claim, wherein the operating conditions, in use, are at stresses of less than 35MPa, at a frequency of at least 0.1 Hz and with amplitudes comprising small angular motions of less than $\pm 12^\circ$ rotation.

9. A method of constructing a self-lubricating bearing comprising the steps of:

- providing a self-lubricating liner with a curved surface;
- providing a counterface having a curved surface;
- electrolytically grinding the curved surface of the counterface to a surface finish of less than 20nm to produce a counterface surface having a hardness of less than 1000VPN; and
- placing the curved surfaces of the liner and the counterface surface in sliding contact with one another.

10. A method according to Claim 8, wherein the curved surfaces are correspondingly curved surfaces.

11. A method of operating a self-lubricating bearing having a self-lubricating liner and a counterface surface in close sliding contact therewith, the counterface surface having a surface finish of less than 20nm and a hardness of less than 1000VPN, wherein the operating conditions are at stresses of less than 35MPa, at a frequency of at least 0.1 Hz and with amplitudes comprising small angular motions of less than $\pm 12^\circ$ rotation.

12. A self-lubricating bearing substantially as hereinbefore described with reference to and as shown in the accompanying drawings.

13. A method of constructing or operating a self-lubricating bearing substantially as hereinbefore described with reference to and as shown in the accompanying drawings.

5

14. Any novel feature or combination of features disclosed herein.

ABSTRACT**"SELF-LUBRICATING BEARINGS"**

5

A self-lubricating bearing for use in low pressure, high frequency, small amplitude applications and methods of operating and constructing the same, the bearing having a self-lubricating liner and a counterface surface in close sliding contact therewith, the counterface surface having a surface finish of less than 20nm and a hardness of less than in the region of 1000VPN.

10





FIGURE 1

Figure 2





**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.